

GEM Ground Enhancement Material

Power Utilities



Ground Enhancement Material (GEM) is a superior conductive material that solves your toughest grounding problems. It is the ideal material to use in areas of poor conductivity, such as rocky ground, mountain tops and sandy soil. GEM dramatically reduces earth resistance and impedance measurements. Furthermore, GEM may reduce the size of the grounding system where conventional methods are unsatisfactory. Once installed, GEM is maintenance-free, not requiring periodic charging or the presence of water to maintain its conductivity.

Third-party testing has been completed to verify that GEM conforms to IEC® 62561-7. This standard introduces a benchmark for electrical performance and corrosion of earth enhancement materials that has been absent from the industry to date.

nVent ERICO offers GEM Calculator software that provides resistivity values for common GEM applications and can help estimate the amount of GEM required for an installation. It operates in four languages - English, Spanish, French and German - and performs calculations in Imperial or Metric units. The GEM Calculator is available for download on our website at erico.com.

FUNKTIONER

Maintains constant resistance for the life of the system once in its set form

Performs in all soil conditions even during dry spells

Does not require periodic charging treatments or placement

Does not require the continuous presence of water to maintain its conductivity

Fully sets within 3 days, fully cures within 28 days

Does not dissolve, decompose, or leach out with time

Non-corrosive

Reduces vandalism and theft since conductors are hard to remove from concrete

Easy-to-handle 25 lb (11.3kg) bags or buckets

Requires only one person to install

Exceeds IEC® 62561-7 which sets the benchmark for corrosion, leaching, sulfur content, and other environmental regulations

Complies to the U.S. Environmental Protection Agency (EPA) Toxicity Characteristic Leaching Procedure (TCLP), EPA test method 1311

Can be installed using trench or ground rod backfill methods

SPECIFIKATIONER

Unit Weight: 11.360 kg

| Table 1/1 | | | | | | | |
|---------------|---------------|---------------------------------|--|--|--|--|--|
| Katalognummer | Artikelnummer | Packaging | | | | | |
| GEM25A | 163670 | Bag with handles | | | | | |
| GEM25ABKT | | Plastic bucket with locking lid | | | | | |

| Estimated Linear Feet of Ground Conductor Covering with Each Bag of GEM | | | | | | | | | |
|---|------------------------|---------|---------|--|--|--|--|--|--|
| Trench Width | Total Thickness of GEM | | | | | | | | |
| | 10.2 cm | 12.7 cm | 15.2 cm | | | | | | |
| 10 cm | 1.0 m | 0.8 m | 0.7 m | | | | | | |
| 15.2 cm | 0.7 m | 0.5 m | 0.4 m | | | | | | |
| 20.3 cm | 0.5 m | 0.4 m | 0.3 m | | | | | | |
| 25.4 cm | 0.4 m' | 0.3 m | 0.3 m | | | | | | |
| 30.5 cm | 0.3 m | 0.3 m | 0.2 m | | | | | | |

| Suggested Specif | ications | | | | | |
|--------------------------|--|--|--|--|--|--|
| Parameter | Recommended Values | Test Method | | | | |
| Standards Compliance | | Full compliance to IEC 62561-7 EPA Toxicity Characteristic Leaching Procedure (TCLP), test method 1311 | | | | |
| Leaching | Arsenic < 1.5 mg/L, Barium < 60 mg/L, Cadmium < 0.15 mg/L, Chromium < 3.0 mg/L, Lead < 1.5 mg/L, Mercury < 0.06 mg/L, Selenium < 1.0 mg/L | EC 62561-7 EN 12457-2 | | | | |
| Sulfur Content | < 2% | ISO 14869-1 | | | | |
| Resistivity | <2 Ω-cm for powder <20 Ω-cm for mixed and cured material | Compressed powder according to ASTM G187-12 Mixed and cured per ASTM D991-89 | | | | |
| Corrosion Performance | For copper-plated earth electrodes, the polarization resistance shall be > 8 Ω x m2 for aggressive environments For galvanized earth electrodes, the polarization resistance shall be > 7.6 Ω x m2 for aggressive environments | IEC 62561-7, Sec 5.5, aggressive environment | | | | |
| Flexural Strength | 300-450 psi [2070-3100 kPa] | ASTM C293 | | | | |
| Compressive Strength | 100-200 psi [690-1390 kPa] after 672 hours curing time | ASTM C109 | | | | |

| Estimated Bags of GEM for Backfilling Around Ground Rods to a Density of 63.5 lb/ft ³ (1,017 kg/m ³) | | | | | | | | | | | | | | |
|---|-------------|----|-----|----|-----|----|-----|----|----|----|-----|----|-----|--|
| Diameter of Hole | | ft | m | ft | m | ft | m | ft | m | ft | m | ft | m | |
| Inches | Centimeters | 5 | 1.5 | 6 | 1.8 | 8 | 2.4 | 10 | 3 | 15 | 4.6 | 20 | 6.1 | |
| 4 | 10.2 | 2 | 2 | | 2 | | 2 | | 3 | | 4 | | 5 | |
| 6 | 15.2 | 3 | 3 | | 3 | | 4 | | 5 | | 8 | | 10 | |
| 8 | 20.3 | 5 | 5 | | 6 | | 8 | | 9 | | 14 | | 18 | |
| 10 | 25.4 | 7 | 7 | | 9 | | 12 | | 14 | | 21 | | 28 | |
| 12 | 30.5 | 10 | 10 | | 12 | | 16 | | 20 | | 30 | | 40 | |

ADVARSEL

nVent-produkter skal kun installeres og anvendes som angivet i nVents produktvejledninger og træningsmaterialer. Vejledninger er tilgængelige på www.nvent.com og hos din nVent kundeservicerepræsentant. Forkert installation, misbrug, fejlanvendelse eller anden undladelse af fuldt ud at følge nVents instruktioner og advarsler kan medføre funktionsfejl, materielle skader, alvorlige personskader eller død og/eller ugyldiggøre din garanti.

 $^{\triangle}$ WARNING: This product can expose you to chemicals including silica and hexavalent chromium, which are known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.



Vores kraftfulde portefølje af mærker:

CADDY HOFFMAN TRACHTE ERICO ILSCO SCHROFF