

nVent ERICO Cu-Bond Round Conductor

Power Utilities


For decades, nVent ERICO has provided the market with high quality copper-bonded ground rods. nVent ERICO has taken that same concept in ground rods and made this into a revolutionary new grounding conductor. The core of the nVent ERICO Cu-Bond Round Conductor is a low carbon steel grade for improved flexibility in the field. The steel core is plated with nickel then electro-plated with a coating of copper. This electro-plating process helps ensure a long-lasting molecular bond between the copper layer and the steel.

The steel core of the conductor provides theft-deterrent benefits, making the conductor difficult to cut with hand tools. With this steel core, nVent ERICO Cu-Bond Round Conductor is a cost-effective alternative to 100% copper conductor. The copper surface of the conductor provides high conductivity and corrosion resistance properties.

Above grade, the unique properties of nVent ERICO Cu-Bond Round Conductor make it ideal for both horizontal and vertical placement. The conductor is well-suited as a lightning protection conductor when applied in accordance with the IEC 62305-3 Edition 2.0 standard.

In the utility industry, the product can be used as a distribution down-lead conductor or as part of a bonding kit for substation fences or equipment ground risers back to the grid. In telecom applications, the product can be used to connect an equipment ground to the ground grid, as a riser (down-lead) for towers, or as a grounding conductor for datacenter mesh bonding. They are also well suited for rail applications such as trackside bonding conductors and stray current conductors, grounding kits for trackside equipment, electrical traction power, as well as in substation, wayside shelters, and communication antenna equipment.

Below grade, nVent ERICO Cu-Bond Round Conductors are ideal as earthing and bonding conductors where copper theft may occur. They may be used as a buried ground grid conductor or electrode for wireless telecom towers, power distribution and transmission grounding in utility substations, large scale ground mount solar farms, petrochemical and mining infrastructure in industrial facilities,



and railway applications. The conductor also can be used as an interconnecting grounding conductor between wind towers or as a grounding grid at the base of a wind tower.

ZERTIFIZIERUNGEN



MERKMALE

Theft-deterrent; steel core is hard to cut with hand tools

Cost-effective; copper bonded to a steel core minimizes the amount of copper in the cable

Superior corrosion resistance; application life of typically 30-40 years in most soil conditions

Copper-bonded coating will not crack or tear when the conductor is bent

High resistance to corrosion and provides a low-resistance path to ground

nVent ERICO Cu-Bond Round Conductor is marked every meter (3.28') for easy measurement in the field

Meets the requirements of IEC® 62305-3 Edition 2 and IEC/EN 62561-2 for lightning protection applications

nVent ERICO Cu-Bond Round Conductors are UL certified to IEC® 62561-2

SPEZIFIKATIONEN

Table 1/1

Katalognummer	Schichtdicke	Äquivalenz der Schmelzfähigkeit	Leitercode von nVent ERICO Cadweld	Stückgewicht	Zertifizierungsdetails
CBSC8	254 µm	25 mm ²	T1	39 kg	IEC 62561-2

ZUSÄTZLICHE PRODUKTDDETAILS

Resistance per unit length measurements made in mΩ/m, CBSC compared with respect to AWG/Metric.


The IEEE® 837 standard (Annex C) provides a method of calculating the fusing current for conductors. This chart is a reference of the calculations for copper-bonded steel conductor according to the IEEE 837 standard. This information is for reference only.

Leiter - Vergleich der physischen Größe		
Kabelschutzleitergröße	Ungefährer Durchmesser	Querschnitt
25 mm ²	6,76 mm	-
35 mm ²	7,65 mm	-
CBSC8	8,00 mm	50,27 mm ²
50 mm ²	8,89 mm	-
CBSC10	10,00 mm	78,52 mm ²
70 mm ²	10,69 mm	-
95 mm ²	12,47 mm	-
CBSC13	13,20 mm	138,07 mm ²
CBSC14	14,20 mm	158,90 mm ²
120 mm ²	14,22 mm	-
CBSC16	15,70 mm	199,84 mm ²
150 mm ²	15,75 mm	-
185 mm ²	17,65 mm	-
CBSC18	17,70 mm	243,27 mm ²

Leitfähigkeitsvergleich				
Teilenummer	AWG (Ω/km)	CBSC Widerstand pro Längenvergleich	mm ² (Ω/km)	CBSC Widerstand pro Längenvergleich
CBSC18	1/0 AWG	118,52 %	50 mm ²	110,82 %
	2 AWG	74,54 %	35 mm ²	77,57 %
CBSC16	2 AWG	102,20 %	35 mm ²	106,36 %
	4 AWG	64,27 %	25 mm ²	75,97 %
CBSC14	2 AWG	137,78 %	25 mm ²	102,42 %
	4 AWG	86,65 %	16 mm ²	65,55 %
CBSC13	2 AWG	134,46 %	25 mm ²	99,95 %
	4 AWG	84,56 %	16 mm ²	63,97 %
CBSC10	4 AWG	132,25 %	16 mm ²	100,05 %
	6 AWG	83,17 %	10 mm ²	62,53 %
CBSC8	6 AWG	107,85 %	16 mm ²	129,73 %
	8 AWG	67,83 %	10 mm ²	81,08 %

Schmelzstrom I rms (kA) - IEEE® 837 Anhang C							
Leiterart Verkupfert, Stahlkern, Gewindestange		CBSC8	CBSC10	CBSC13	CBSC14	CBSC16	CBSC18
Leiterquerschnitt in mm ²	A	50.265	78.52	138.07	158.903	199.84	243.27
Anfängliche Leitertemperatur in °C	Ta	40	40	40	40	40	40
Zeit des Stromflusses in Sekunden	tc	2	2	2	2	2	2
Maximal zulässige Temperatur in °C	Tm	1084	1084	1084	1084	1084	1084
Wärme­koeffizient des spezifischen Widerstands bei Referenztemperatur Tr	ar	0.00378	0.00378	0.00378	0.00378	0.00378	0.00378
Widerstand des Erdleiters bei Referenztemperatur Tr in m und -cm	rr	8.621	8.621	8.621	8.621	8.621	8.621
1 / a 0 oder (1 / a r) - Tr in ° C	K0	245	245	245	245	245	245
Wärmekapazitätsfaktor in Joule / cm ³ / ° C	TCAP	3.846	3.846	3.846	3.846	3.846	3.846
Leitfähigkeit des Materials	%	24.5	20.4	18.8	15.9	16.3	17.7
Sicherungsstrom-Berechnung	β	84.73	84.73	84.73	84.73	84.73	84.73
	I	4.79	7.48	13.16	15.15	19.05	23.19
	I90 %	4.31	6.74	11.84	13.63	17.14	20.87
	I80 %	3.83	5.99	10.53	12.12	15.24	18.55

DIAGRAMME



WARNUNG

nVent-Produkte müssen in Übereinstimmung mit den Produktinformationsblättern und dem Schulungsmaterial von nVent installiert und verwendet werden. Informationsblätter sind verfügbar unter www.nVent.com sowie bei Ihrem nVent-Kundendienstvertreter. Unsachgemäße Installation, Missbrauch, Fehlanwendung oder andere Handlungen im Widerspruch zu den Anweisungen und Warnungen von nVent können zu Fehlfunktionen, Anlagenschäden, schwerer Körperverletzung sowie zum Tod führen und/oder haben die Annullierung der Garantie zur Folge.

⚠ WARNING: This product can expose you to chemicals including lead, which is known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.



Unser starkes markenportfolio:

CADDY ERICO HOFFMAN ILSCO SCHROFF TRACHTE

©2025 nVent. Alle Marken und Logos von nVent sind Eigentum der nVent Services GmbH oder ihrer Tochtergesellschaften oder durch sie lizenziert. Alle übrigen Marken sind Eigentum ihrer jeweiligen Inhaber. nVent behält sich das Recht vor, ohne Vorankündigung Änderungen vorzunehmen.

Dieses Dokument ist systemgeneriert.